

PROFESSIONAL

WOOD - PRODUCT DATASHEET 2023



TECHNICAL DATA (EN 13489)		14 mm
Reaction to fire	EN 14342 Table 1 (when applicable) / EN 13501	Dfl-s1
Emission of formaldehyde	EN 14342	E1
Brinell hardness (average value) Ash Oak	(BHN) EN1534	4,0 3,7
Taber Abraser/Lacquer's wear resistance Protoco Lacquer Protoco Natura <i>These typical values are not applicable for stained, brushed or hardwax oiled products.</i>	EN 13696	4000 3500
Reduction of sound weighted index ΔL_w in dB with 2 mm Tarkofoam/flex II	EN ISO 10140-3 / EN ISO 717-2	≥ 17
Thermal insulation value (RT m ² K/W) board only with rag felt with 2 mm Tarkofoam/flex II	EN ISO 10456:2007	0,101 0,121 0,141
Thermal conductivity (W/m K)	EN 12664 / EN 14342:2013	0,11
Construction: softwood veneer and lamella core		3-layer

INSTALLATION	
Installation method	2-lock for floating or glue down
Installation instruction	Download from www.tarkett.com Contact your supplier for more details
Underfloor heating compatible Maximum floor surface temperature 27°C with self-regulating underfloor heating system	Yes
Start & Stop: Shorter lengths of planks included in approx. 1 pack per 20 m ²	

RECOMMENDED ACCESSORIES	
Installation	Tarkofoam II / Tarkoflex II Installation kit
Aesthetics	Skirting Transition moulding Pipe covers
Care & Maintenance	Tarkoclean Refresher (for lacquered floors)
See more alternatives and the complete range of accessories @ www.tarkett.com	

MAINTENANCE
These Tarkett wooden floors have a Protoco surface treatment and therefore a strong protection against normal wear, abrasion, scratches and stains. Some floors will require more frequent maintenance for increased life span. Generally these products are light coloured floors and hardwax oiled floors, particularly with brushed surface and/or high-lighted details. Please always refer to maintenance guidance available on websites.
See maintenance instructions @ www.tarkett.com



PROFESSIONAL

WOOD - PRODUCT DATASHEET 2023

PRODUCT DATA	Material code	Dimensions LxWxH (mm)	Pattern	Surface treatment	Surface effect	Bevel	Character	Latin name	DoP no.	Wear layer thk (mm)	Board/ pack	m2/ pack	m2/ pallet	Net weight/ m2 (kg)
Ash Nature White TreS	7965019	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Lively	2	0020-0106	3,5	6	2,66	93,10	7,9
Ash Contrast White TreS	7965017	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Expressive	2	0020-0106	3,5	6	2,66	93,10	7,9
Ash Nature TreS	7965018	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Lively	2	0020-0106	3,5	6	2,66	93,10	7,9
Ash Contrast TreS	7965016	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Expressive	2	0020-0106	3,5	6	2,66	93,10	7,9
Oak Nature White TreS	7870079	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Calm	1	0020-0106	3,5	6	2,66	93,10	7,9
Oak Robust White TreS	7870081	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Lively	1	0020-0106	3,5	6	2,66	93,10	7,9
Oak Nature TreS	7870077	2 281 x 194 x 14	3-strip	Proteco Lacquer	-	-	Calm	1	0020-0106	3,5	6	2,66	93,10	7,9
	7870078	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Calm	1	0020-0106	3,5	6	2,66	93,10	7,9
Oak Nature TreS 2027	8721007	2 027 x 194 x 14	3-strip	Proteco Natura	-	-	Calm	1	0020-0106	3,5	6	2,36	94,40	7,9
Oak Robust TreS	7870080	2 281 x 194 x 14	3-strip	Proteco Natura	-	-	Expressive	1	0020-0106	3,5	6	2,66	93,10	7,9

Due to the nature of the material this table shows typical values.

1: Quercus Robur & Quercus Petraea, 2: Fraxinus Angustifolia



Professional Ash Nature White TreS



Professional Ash Contrast White TreS



Professional Ash Nature TreS



Professional Ash Contrast TreS



Professional Oak Nature White TreS



Professional Oak Robust White TreS



Professional Oak Nature TreS



Professional Oak Nature TreS 2027



Professional Oak Robust TreS

The pictures only present the colour of the floor. For more details regarding grading and variations see the Grading Book or www.tarkett.com. Tarkett's international range of floors comprises many different products. Some of these may not be for sale in your country. Although every care has been taken to reproduce images that reflect the finished product, the quality of monitor and printer and the nature of wood results in variations in the color and structure of individual planks. When sanding a wooden floor the appearance will change in colour, texture and surface effects.

For further and latest information please visit www.tarkett.com